

MARKED-UP VERSION OF
ENGLISH TRANSLATION OF
INTERNATIONAL APPLICATION
AS ORIGINALLY FILED

~~DESCRIPTION~~

Attorney Docket No. 36856.1453

LAMINATED COIL

~~Technical~~BACKGROUND OF THE INVENTION

1. Field of the Invention

[0001] —The present invention relates to a laminated coil and, more specifically, ~~relates~~ to an open magnetic path type laminated coil having an excellent direct current (DC) superposition characteristic.

~~Background~~2. Description of the Related Art

[0002] —An open magnetic path type laminated coil has been proposed as a known laminated coil in order to prevent a sudden decrease in the inductance value due to magnetic saturation inside a magnetic body. As described in Japanese Examined Patent Document~~Application~~ Publication No. 1-35483, an open magnetic path type laminated coil includes a non-magnetic layer provided inside a laminated coil ~~consisting of~~including magnetic layers. According to the structure of the open magnetic path type laminated coil, magnetic ~~fluxes~~ leakflux leaks from ~~parts~~portions in the magnetic layers to the outside of the laminated coil, making it difficult for magnetic saturation to occur inside the magnetic body. As a result, reduction in inductance caused by a direct current is reduced, and the DC superposition characteristic is

improved.

[0003] — Although the open magnetic path type laminated coil according to Japanese Examined Patent Document ~~1~~Application Publication No. 1-35483 has an excellent DC superposition characteristic, there is a problem in that the inductance characteristic is unsatisfactory. In other words, since the non-magnetic layer is disposed at a ~~position~~ on location along the path of magnetic fluxes, the magnetic ~~fluxes are~~ flux is blocked, causing a reduction in inductance. To obtain the desired inductance, the inductance may be increased by increasing the ~~coil-number of~~ coil turns. However, an increase in the ~~coil-number of~~ coil turns causes the direct current resistance to be significantly increased.

~~Patent Document 1: Japanese Examined Patent Application Publication No. 1-35483~~

~~Disclosure of Invention~~

~~— The~~

SUMMARY OF THE INVENTION

[0004] To overcome the problems described above, preferred embodiments of the present invention provides a laminated coil that has an excellent DC superposition characteristic and that is capable of ~~suppressing~~ preventing the reduction of inductance while reducing the direct current resistance.

[0005] — A laminated coil according to a preferred

embodiment of the present invention includes:~~(a)~~ a laminated body including magnetic body sections provided on both main surfaces of a non-magnetic body section, the magnetic body sections ~~formed by stacking~~ including a plurality of stacked magnetic layers, the non-magnetic body section including at least one layer of a non-magnetic layer~~,~~ and ~~(b)~~ a coil including coil conductors provided in the laminated body, the coil conductors being helically connected~~,~~ wherein~~,~~ ~~(c)~~ the conductor width of at least one of the coil conductors provided inside the non-magnetic body sections and the coil conductors provided on both main surfaces of the non-magnetic body sections of the coil conductors provided in the laminated body is greater than the conductor width of the other coil conductors.

[0006] — Since the conductor width of at least one of the coil conductors provided inside the non-magnetic body sections and the coil conductors provided on both main surfaces of the non-magnetic body sections is greater than the conductor width of the other coil conductors, the direct current resistance ~~can be~~ is reduced. Since coil conductors having a ~~great~~ greater conductor width are provided inside the non-magnetic body sections and/or on both main surfaces, reduction in inductance ~~can be reduced~~ is suppressed even when the conductor width of the coil conductors is increased.

[0007] — More specifically, in general, if the conductor width of the coil conductors is increased, magnetic fluxes of the coil is blocked by the coil

conductors having a ~~great~~greater conductor width and the inner circumference of the coil is reduced such that the amount of magnetic fluxes of the coil is reduced. Therefore, inductance is reduced. However, even if the conductor width of the coil conductors of the non-magnetic body section is increased, the amount of magnetic fluxes of the coil blocked by increasing the conductor width of the coil conductors is ~~significantly~~sufficiently small ~~since~~because the magnetic fluxes of the coil ~~are~~is blocked by the non-magnetic body section from the beginning. Furthermore, even if the ~~if~~the conductor width of the coil conductors is increased, the reduction in the amount of magnetic fluxes transmitted is small compared with the reduction in the inner circumference of the coil at the magnetic body sections transmitting the magnetic fluxes because the inner circumference of the coil at the non-magnetic body section that blocks the magnetic fluxes is reduced. Thus, the reduction ~~of~~in the induction of the entire coil ~~can be~~is reduced.

[0008] ——According to ~~the laminated coil according the~~
preferred embodiments of the present invention, the conductor width of the coil conductors provided inside the non-magnetic body sections and the coil conductors provided on both main surfaces of the non-magnetic body sections ~~may be~~are greater than the conductor width of the other coil conductors. By increasing the conductor width of the coil conductors provided inside the non-magnetic body sections and the coil conductors provided on both main surfaces of

the non-magnetic body sections, a plurality of coil conductors having ~~a great~~ an increased conductor width is provided. Thus, the direct current resistance ~~can be~~ is significantly reduced.

[0009] ~~According to the laminated coil according the present invention, it is desirable that the~~ The conductor width of the coil conductors having a great conductor width is preferably about 1.05 to about 2.14 times the conductor width of the other coil conductors. In this ~~way~~ manner, a coil ~~whose~~ of which reduction in inductance is ~~reduced~~ suppressed as much as possible and whose direct current resistance is significantly reduced ~~can be~~ is obtained.

[0010] ~~According to the laminated coil according the present invention, a~~ A plurality of the non-magnetic body sections may be provided inside the laminated body. By providing a plurality of the non-magnetic body sections inside the laminated body, the amount of magnetic fluxes leaking from the non-magnetic body section to the outside of the laminated coil ~~can be~~ is further increased ~~even more~~. Thus, the DC superposition characteristic ~~can be~~ is further improved.

[0011] ~~According to~~ to preferred embodiments of the present invention, a laminated coil having an excellent DC superposition characteristic and being capable of ~~suppressing~~ preventing the reduction of inductance ~~and~~ while reducing the direct current resistance is provided,

~~since~~because the conductor width of the coil conductors provided inside the non-magnetic body sections and the coil conductors provided on both main surfaces of the non-magnetic body sections is greater than the conductor width of the other coil conductors.

[0012] Other features, elements, steps, characteristics and advantages of the present invention will become more apparent from the following detailed description of preferred embodiments of the present invention with reference to the attached drawings.

~~Brief Description of the Drawings~~

BRIEF DESCRIPTION OF THE DRAWINGS

[0013] ——— Fig. 1 is a schematic cross-sectional view of a laminated coil according to a first preferred embodiment of the present invention.

[0014] ——— Fig. 2 is an exploded perspective view of a laminated coil according to the first preferred embodiment of the present invention.

[0015] ——— Fig. 3 is a schematic cross-sectional view of a known laminated coil.

[0016] ——— Fig. 4 is a schematic cross-sectional view of a laminated coil according to a first comparative example.

[0017] ——— Fig. 5 is a schematic cross-sectional view of a laminated coil according to a third preferred embodiment of the present invention.

[0018] ——— Fig. 6 is a schematic cross-sectional view of

a laminated coil according to a fourth preferred embodiment of the present invention.

[0019] ——— Fig. 7 is a schematic cross-sectional view of a laminated coil according to a fifth preferred embodiment of the present invention.

[0020] ——— Fig. 8 is a schematic cross-sectional view of a laminated coil according to a second comparative example.

~~Best Mode for Carrying Out the Invention~~

DETAILED DESCRIPTION OF PREFERRED EMBODIMENTS

[0021] ——— ~~Embodiments~~ Preferred embodiments of a laminated coil according to the present invention will be described below with reference to the drawings.

First Preferred Embodiment

[0022] ——— Fig. 1 is a schematic cross-sectional view of a laminated coil according to a first preferred embodiment of the present invention. The laminated coil includes a laminated body 9 having magnetic body sections 1 and a non-magnetic body section 2, a coil L ~~consisting~~ including helically connected coil conductors 3 and 4 provided on the laminated body 9, and external electrodes 5. The magnetic body sections 1 are provided on both main surfaces of the non-magnetic body section 2. The magnetic body sections 1 each ~~consists~~ include a plurality of magnetic layers, and the non-magnetic body section 2 ~~consists~~ includes one non-magnetic layer.

[0023] —As shown in Fig. 1, the coil conductors 4 are provided on both main surface of the non-magnetic body section 2. The conductor width of the coil conductors 4 is greater than that of the other coil conductors 3 having a predetermined conductor width. Since the conductor width of the coil conductor 4 is ~~great~~increased, the direct current resistance of the laminated coil is reduced.

[0024] —Since the coil conductors 4 each having a ~~great~~an increased conductor width are provided on both main surfaces of the non-magnetic body section 2, reduction ~~of~~in inductance ~~can be reduced~~is suppressed. More specifically, in general, if the conductor width of the coil conductors is increased, inductance is reduced because the amount of transmitted magnetic fluxes of the coil is reduced by being blocked by the coil conductors having a ~~great~~an increased conductor width and by reducing the inner circumference of the coil. However, according to the first preferred embodiment, since the magnetic fluxes of the coil L ~~are~~is blocked by the non-magnetic body section 2 from the beginning, the amount of magnetic fluxes of the coil L that are blocked is significantly reduced by increasing the conductor width of the coil conductors 4 on both main surfaces of the non-magnetic body section 2. Even if the conductor width of the coil conductors 4 is increased, the inner circumference of the coil L in the non-magnetic body section 2 blocking the magnetic fluxes is reduced. Therefore, the reduction in the amount of the transmitted

magnetic fluxes is small compared to the reduction in the inner circumference of the coil L in the magnetic body sections 1 transmitting the magnetic fluxes. In this ~~way,~~ manner, the reduction in induction of the entire coil L ~~can be~~ is significantly reduced.

[0025] ——Next, a method of producing ~~a~~ the laminated ~~coil~~ coil according to the first preferred embodiment is described with reference to an exploded perspective view of a laminated coil illustrated in Fig. 2.

[0026] ——In the method of producing a laminated coil, first, green sheets 6 ~~consisting of~~ including a magnetic material and a green sheet 7 ~~consisting of~~ including a non-magnetic material are produced. After forming the laminated coil, the magnetic green sheets are referred to as magnetic layers and the non-magnetic green sheet is referred to as a non-magnetic layer.

[0027] ——According to the ~~first~~ first preferred embodiment, a Ni-Cu-Zn based material is used as a magnetic material. First, a raw material including about 48.0 mol% of ferric oxide (Fe_2O_3), about 20.0 mol% of zinc oxide (ZnO), about 23.0 mol% of nickel oxide (NiO), and about 9 mol% of copper oxide (CuO) is wet prepared using a ball mill. The obtained mixture is dried and ground. The obtained powder is calcinated at about 750°C for about one hour. The obtained powder is mixed with a binder resin, a plasticizer, a moistening agent, and a dispersant by a ball mill. Then, defoaming is ~~carried out~~ performed to obtain slurry. The

slurry is applied onto a peelable film. Then, by drying, the magnetic green sheet 6 that has a predetermined thickness is produced.

[0028] —As a non-magnetic material, a Cu-Zn based material is preferably used. The non-magnetic green sheet 7 is produced of a raw material including about 48.0 mol% of Fe_2O_3 , about 43.0 mol% of ZnO, and about 9.0 mol% of copper oxide (CuO) and preferably by ~~employing~~using the same method as that of the above-described magnetic material. The relative magnetic permeability of a green sheet is about 130 for the magnetic green sheet 6 and about 1 for the non-magnetic green sheet 7.

[0029] —Next, the green sheets 6 and 7 obtained as described above are cut into predetermined sizes. After stacking the green sheets 6 and 7, through-holes are formed at predetermined ~~positions~~locations by ~~employing~~ a laser method ~~so~~such that the helical coil L is formed. Then, the coil conductors 3 and 4 are formed by applying conductive paste ~~mainly consisting of~~primarily including silver or a silver alloy onto magnetic green sheets 6a and the non-magnetic green sheet 7 by a ~~method of~~ screen printing method. By filling the inside of the through-holes with the conductive paste simultaneously to the production of the coil conductors 3 and 4, via-hole connection conductors 8 ~~for connection can be~~ are easily formed.

[0030] —Here, the coil conductors 4 having a ~~great~~an increased width are formed on both main surfaces of the non-

magnetic green sheet 7. According to the first preferred embodiment, the coil conductors 4 having a ~~great~~an increased width are produced ~~so~~such that the conductor width is about 550 μm and the other coil conductors 3 are produced ~~so~~such that the conductor width is about 350 μm after calcination. By forming the coil conductors 4 having a ~~great~~an increased width on both main surfaces of the non-magnetic green sheet 7, a laminated coil capable of suppressing the reduction in inductance and reducing direct current resistance ~~can be~~is obtained.

[0031]——Subsequently, the laminated body is produced by stacking the magnetic green sheets 6a having the coil conductors 3 on both main surfaces of the non-magnetic green sheet 7 and by disposing exterior magnetic green sheets 6b, not having coil conductors on the top and bottom. At this time, by stacking the non-magnetic green sheet 7 at a ~~position~~location substantially in the middle along the axial center direction of the helical coil L, the amount of magnetic fluxes leaking outside the laminated coil is increased. Thus, the DC superposition characteristic ~~can be~~is improved.

[0032]——Then, the laminated body is pressure bonded at about 45°C at a pressure of about 1.0 t/cm² and cut into pieces of 3.2×2.5×0.8 mm by a dicer or a guillotine cutter to obtain unfired bodies of the laminated coil.

Subsequently, binder removal and firing of the unfired bodies are ~~carried out~~performed. For binder removal, the

unfired bodies are fired in a low oxygen atmosphere at about 500°C for about 2 hours. For firing, the bodies are fired in an atmosphere of about 890°C for about 150 minutes. Finally, conductive paste ~~mainly consisting of~~ primarily including silver is applied by immersion to the end surfaces where the lead electrodes 4a and 4b are exposed. After drying the bodies at about 100°C for about 10 minutes, baking is ~~carried out~~ performed at about 780°C for about 150 minutes. In this ~~way~~ manner, the laminated coil according to the first preferred embodiment is obtained.

Table 1

	Rdc ($m\Omega$)	Inductance (μH)
Conventional Example	185	2.00
First Embodiment	166	1.91
First Comparative Example	150	1.56

[0033] ———Table 1 shows the results of tests ~~carried out~~performed to confirm the advantages of the laminated coil according to the first preferred embodiment produced as described above. As shown in Fig. 3, ~~according to~~in the laminated coil according to the conventional example, the conductor width of each of the coil conductors 13 provided on magnetic body sections 11 and a non-magnetic body section 12 is about 350 μm . As shown in Fig. 4, ~~according to~~with the laminated coil according to the comparative example, each of the conductor width of coil conductors 24 provided on magnetic body sections 21 and a non-magnetic body section 22 is broader, about 550 μm . For every laminated coil, the ~~coil~~-number of coil turns of the helical coil L is about 5.5 turns, and the size of the laminated coil is 3.2×2.5×2.5 mm.

[0034] ———According to Table 1, for the laminated coil according to the first preferred embodiment, the direct current resistance is reduced and the reduction of inductance is relatively small. More specifically, the direct current resistance of the conventional example is

about 185 mΩ, whereas the direct current resistance of the first preferred embodiment is about 166 mΩ and is reduced by about 10%. The inductance of the conventional example is about 2.0 μH, whereas the inductance of the first preferred embodiment is about 1.91 μh and is ~~only~~ reduced by about 4.5%. In contrast, according to the comparative example in which the conductor width of all coil conductors is increased, the direct current resistance is reduced by about 18% to about 150 mΩ and the inductance is greatly reduced by about 22% to about 1.56 μH. In this ~~way~~manner, according to the first preferred embodiment, the reduction of inductance ~~can be~~is suppressed while the direct current resistance is reduced by increasing the conductor width of the coil conductors 4 because the coil conductors 4 having ~~a great~~an increased conductor width are provided on both main surfaces of the non-magnetic body section 2 ~~that is~~ blocking the magnetic fluxes.

Table 2

	Conductor Width of Coil Conductors disposed on Both Main Surfaces of Non-magnetic Body	Conductor--Width Ratio <u>between</u> <u>Coil Conductors</u> <u>disposed on Both</u> <u>Main Surfaces of</u> <u>Non-magnetic</u> <u>Body and those</u> <u>which are not</u> <u>disposed thereon</u>	Rdc (mΩ)	Inductance
Conventional Example	350 μm	1.00	185	2.00
Specimen 1	357 μm	1.02	184	2.00
Specimen 2	368 μm	1.05	183	1.99
Specimen 3	450 μm	1.29	176	1.96
Specimen 4	550 μm	1.57	166	1.91
Specimen 5	650 μm	1.86	157	1.86
Specimen 6	750 μm	2.14	147	1.79
Specimen 7	850 μm	2.43	138	1.71

[0035] —Next, Table 2 shows the evaluation results of specimens 1 to 7, wherein the conductor widths of the coil conductors 4 provided on both main surfaces of the non-magnetic body section 2 are changed. The specimens 1 to 7 were produced ~~so~~such that the conductor widths of the coil conductors 4 provided on both main surfaces of the non-magnetic body section 2 differ and are about 357 μm, about

368 μm, about 450 μm, about 550 μm, about 650 μm, about 750, and about 850 μm, respectively. ~~The conductor~~
Meanwhile, the width (i.e., 350 μm) of each conductor in the
laminated coil according to the conventional example, is
the same, i.e., 350 μm, as shown in Fig. 3.

[0036] — For the specimens 2 to 6, the direct current resistance is reduced and the inductance values are desirable. The specimen 1 (conductor width ratio of about 1.02) exhibited a significantly small reduction of less than about 1% in the direct current resistance. For the specimen 7 (conductor width ratio of about 2.43), reduction in the inductance value compared with that of the conventional example is significantly ~~reduced to~~ suppressed by about 14.5%.

Second Preferred Embodiment

[0037] — The structure of a laminated coil according to a second preferred embodiment of the present invention preferably is substantially the same as the structure of the laminated coil according to the first preferred embodiment illustrated in Fig. 1. However, for a laminated coil according to the second preferred embodiment, the conductor width of the coil conductors 4 disposed on both main surfaces of the non-magnetic body section 2 is about 750 μm, and the conductor width ~~3~~ of the coil conductors 3 that are not disposed on both main surfaces of the non-magnetic body section 2 is about 350 μm. The conventional example ~~7~~ shown in Table 3 below ~~7~~ represents a laminated coil whose coil

conductors 13 provided on magnetic body sections 11 and a non-magnetic body section 12, ~~as shown in Fig. 3,~~ all have a conductor width of about 350 μm , as shown in Fig. 3. The second comparative example, as shown in Fig. 8, represents a laminated coil whose coil conductors 34 that are not provided on both main surfaces of a non-magnetic body section 32 (or, provided inside magnetic body sections 31) have a conductor width greater than that of other coil conductors 33. The conductor width of the coil conductors 34 having ~~a great~~ an increased conductor width is about 750 μm . The conductor width of the coil conductors 33 is about 350 μm .

Table 3

	Rdc ($\text{m}\Omega$)	Inductance (μH)
Conventional Example	185	2.00
Second Embodiment	147	1.79
Second Comparative Example	147	1.53

[0038] ———For the laminated coil according to the second preferred embodiment, as shown in Table 3, the direct current resistance is reduced as compared with to the conventional example because the conductor width of the coil conductors 4 that are disposed on both main surfaces of the non-magnetic body section 2 is ~~great.~~ increased. Furthermore, for the laminated coil according to the second comparative

example, the direct current resistance is reduced as compared ~~with~~to the conventional example because the conductor width of the coil conductors 34 ~~having~~, as many as the same coil turn number as that of the laminated coil according to the second embodiment, is increased. The inductance of the laminated coil according to the second preferred embodiment is about 1.79 μ h and is only reduced by about 10% as compared withto the conventional example. The inductance of the laminated coil according to the second comparative example is about 1.53 μ m and is reduced by about 23% as compared withto the conventional example. The reduction of the inductance of the laminated coil according to the second preferred embodiment ~~can be~~ is suppressed because the coil conductors 4 having a ~~great~~ greater conductor width are provided on both main surfaces of the non-magnetic body section 2 that blocks the magnetic fluxes.

Third Preferred Embodiment

[0039] ——— Fig. 5 illustrates a schematic cross-sectional view of a laminated coil according to a third preferred embodiment of the present invention. In Fig. 5, the components that are the same as or correspond to those in Fig. 1 are represented by the same reference numeral as those in Fig. 1, and descriptions thereof are not repeated.

[0040] ——— In the laminated coil according to the third preferred embodiment, the coil conductors 4 are ~~formed~~ provided inside the non-magnetic body section 2. The

conductor width of the coil conductors 4 is greater than the conductor width of the other coil conductors 3. Similar to the first preferred embodiment, the laminated coil according to the third preferred embodiment is produced through steps of stacking and pressure bonding green sheets having coil conductors, cutting the green sheets into chips, and forming external electrodes.

[0041] —By providing the coil conductors 4 having a ~~great~~an increased conductor width, the direct current resistance ~~can be~~is reduced. Furthermore, by forming the coil conductors 4 having a ~~great~~an increased conductor width inside the non-magnetic body section 2, the reduction of inductance ~~can be~~is reduced.

Fourth Preferred Embodiment

[0042] —Fig. 6 illustrates a schematic cross-sectional view of a laminated coil according to a fourth preferred embodiment. In Fig. 6, the components that are the same as or correspond to those in Fig. 1 are represented by the same reference numeral as those in Fig. 1, and descriptions thereof are not repeated.

[0043] —In the laminated coil according to the fourth preferred embodiment, the coil conductors 4 are ~~formed~~provided inside the non-magnetic body section 2 and on both main surfaces of the non-magnetic body section 2. The conductor width of the coil conductors 4 is greater than the conductor width of the other coil conductors 3.

[0044] —By providing the coil conductors 4 with a ~~greater~~ increased conductor width, the direct current resistance ~~can be~~ is reduced. In particular, according to the fourth preferred embodiment, since three layers of the coil conductors 4 having a ~~greater~~ increased conductor width are provided, the direct current resistance ~~can be~~ is significantly reduced. By forming the coil conductors 4 having a ~~greater~~ increased conductor width inside the non-magnetic body section 2 and on both main surfaces of the non-magnetic body section 2, the reduction of inductance ~~can be~~ is reduced.

Fifth Preferred Embodiment

[0045] —Fig. 7 illustrates a schematic cross-sectional view of a laminated coil according to a fifth preferred embodiment. In Fig. 7, the components that are the same as or correspond to those in Fig. 1 are represented by the same reference numeral as those in Fig. 1, and descriptions thereof are not repeated.

[0046] —In the laminated coil according to the fifth preferred embodiment, two of the non-magnetic body sections 2 are provided inside the laminated body 9. The coil conductors 4 are provided on both sides of the non-magnetic body sections 2. The conductor width of the coil conductors 4 is greater than the conductor width of the other coil conductors 3.

[0047] ——— Since two of the non-magnetic body sections 2 are provided inside the laminated body 9, the amount of magnetic fluxes leaking outside the laminated coil ~~can be~~ is increased, and the DC superposition characteristic ~~can be~~ is improved. By providing wide coil conductors 4, the direct current resistance ~~can be~~ is reduced. In particular, according to the fifth preferred embodiment, since four layers of the coil conductors 4 having ~~a great~~ an increased conductor width are provided, the direct current resistance ~~can be~~ is significantly reduced. By providing coil conductors 4 having ~~a great~~ an increased conductor width on both main surfaces of the non-magnetic body sections 2, the reduction of inductance ~~can be~~ is reduced.

——— ~~Other Embodiments~~

[0048] ——— The laminated coil according to preferred embodiments of the present invention is not limited to the above-described preferred embodiments, and various modifications may be ~~employed~~ made and still fall within the scope of the present invention.

[0049] ——— For example, the conductor width of one of the coil conductors provided on both main surfaces of the non-magnetic body section may be ~~great~~ increased. The conductor width of at least one of the coil conductors provided inside the non-magnetic body section and on both main surfaces of the non-magnetic body section may be greater than the conductor width of the other coil conductors in the main

sections.

~~Industrial Applicability~~

~~[0001]~~———As described above, the present invention may be ~~employed to~~used for an open magnetic path type laminated coil and, in particular, is advantageous in that the DC superimposition characteristic is excellent, reduction in inductance ~~can be~~is reduced, and direct current resistance ~~can be~~is reduced.

[0050] While preferred embodiments of the present invention have been described above, it is to be understood that variations and modifications will be apparent to those skilled in the art without departing the scope and spirit of the present invention. The scope of the present invention, therefore, is to be determined solely by the following claims.